



Kottinu™ heat resistance test results.

The ISO 17493:2000 test substantiates that the thermal stability of Kottinu™ exceeds the 400°F requirement of section 31.15 of the Occupational Health and Safety Regulation (British Columbia) standards by a wide margin.

Heat Resistance	400°F	450°F
Melt	No Change	No Change
Drip	No Change	No Change
Ignite	No Change	No Change
Break	No Change	No Change
	EN ISO 11612:2008 6.2.2 ISO 17493:2000 (400± 5)° FX 5min	EN ISO 11612:2008 6.2.2 ISO 17493:2000 (450± 5)° FX 5min